

GPI Series I-Joists
Georgia-Pacific Wood Products LLC

PR-L255
Revised August 21, 2008

Products: GPI 20, 40 and 65 Series I-Joists
Georgia-Pacific Wood Products LLC, 1000 North Park Drive, Roxboro, North Carolina 27573
(336) 599-1000
www.gp.com

1. Basis of the product report:
 - 2006 International Building Code: Section 104.11 Alternative Materials
 - 2006 International Residential Code: Section R104.11 Alternative Materials
 - ASTM D 5055-04 recognized by the 2006 IBC and IRC
 - APA Reports T1999P-07, T1999P-24, T2001M-1, T2001M-89, T2002M-60A, T2003M-43, T2003M-44A, T2003M-55, T2003M-78, T2004M-44, T2005M-10, T2005M-53, T2006M-71, T2007M-29, T2007M-65, T2007M-108, and other qualification data
2. Product description:

GPI Series I-joists are made with laminated veneer lumber (LVL) flanges and an OSB web in accordance with the in-plant manufacturing standard approved by APA.
3. Design properties:

Table 1 lists the design properties for GPI Series I-joists. The allowable spans for GPI Series I-joists shall be in accordance with the recommendations provided by the manufacturer (www.gp.com/build/product.aspx?pid=1390).
4. Product installation:

GPI Series I-joists shall be installed in accordance with the recommendations provided by the manufacturer (see link above). Permissible web holes and cantilever reinforcements shall be in accordance with the recommendations provided by the manufacturer.
5. Fire-rated assemblies:

Fire-rated assemblies shall be constructed in accordance with the recommendations provided by the manufacturer (see link above), and with APA Design/Construction Guide: *Fire-Rated Systems*, Form W305 (www.apawood.org/publications).
6. Limitations:
 - a) GPI Series I-joists shall be designed in accordance with the code using the design properties specified in this report.
 - b) GPI Series I-joists are limited to dry service conditions where the average moisture content is less than 16 percent.
 - c) GPI Series I-joists are produced at the Georgia-Pacific Wood Products LLC, Roxboro, North Carolina facilities under a quality assurance program audited by APA.
 - d) This report is subject to reexamination in 1 year.
7. Identification:

The GPI prefabricated wood I-joists described in this report are identified by a label bearing the manufacturer's name (Georgia-Pacific Wood Products LLC) and/or trademark, the APA assigned plant number (1027), the I-joist depth and series, the APA-EWS logo, the report number PR-L255, and a means of identifying the date of manufacture.

Table 1. Design Properties (Allowable Stress Design) for GPI Series I-Joists ^(a,b)

Joist Depth (in.)	Joist Series	EI ^(c) (x10 ⁶ lbf-in. ²)	M ^(d) (lbf-ft)	V ^(e) (lbf)	End Reaction ^(f) (lbf)				Intermediate Reaction (lbf)				C ^(g) (x10 ⁶ ft-lb/in.)
					1-3/4 in. Brg. Length		4 in. Brg. Length		3-1/2 in. Brg. Length		5-1/4 in. Brg. Length		
					w/o Brg. Stiff	w/Brg. Stiff	w/o Brg. Stiff	w/Brg. Stiff	w/o Brg. Stiff	w/Brg. Stiff	w/o Brg. Stiff	w/Brg. Stiff	
9-1/2	GPI 20	159	3,000	1,135	1,050	---	1,135	---	2,340	2,495	3,000	3,145	0.412
	GPI 40	193	3,090	1,200	1,120	---	1,200	---	2,600	2,650	3,025	3,150	0.412
	GPI 65	254	4,900	1,210	1,120	---	1,210	---	2,610	2,700	3,070	3,175	0.412
11-7/8	GPI 20	274	3,870	1,435	1,100	---	1,435	---	2,340	2,640	3,000	3,170	0.515
	GPI 40	330	3,990	1,460	1,225	---	1,460	---	2,600	2,750	3,025	3,175	0.515
	GPI 65	434	6,325	1,495	1,230	---	1,495	---	2,610	2,800	3,070	3,200	0.515
14	GPI 20	409	4,640	1,710	1,150	1,225	1,690	1,710	2,340	2,800	3,000	3,195	0.607
	GPI 40	482	4,790	1,715	1,250	---	1,715	---	2,600	2,850	3,025	3,200	0.607
	GPI 65	640	7,605	1,740	1,335	---	1,740	---	2,610	2,900	3,070	3,225	0.607
16	GPI 40	657	5,550	1,990	1,235	1,350	1,550	1,990	2,600	2,950	3,025	3,225	0.693
	GPI 65	877	8,755	2,000	1,345	1,575	1,650	2,000	2,610	3,000	3,070	3,250	0.693

For SI: 1 inch = 25.4 mm, 1 foot = 304.8 mm, 1 lbf = 0.454 kg.

- (a) The tabulated values are design values for normal duration of load. All values, except for EI and C, shall be permitted to be adjusted for other load durations as permitted by the code.
- (b) The maximum vertical load transfer of GPI Series I-Joists is 2,000 plf.
- (c) Bending stiffness (EI) of the I-joist.
- (d) Moment capacity (M) of the I-joist, which shall not be increased by any repetitive member use factor.
- (e) Shear capacity (V) of the I-joist.
- (f) Interpolation of the end reaction between 1-3/4- and 4-inch bearing is permitted.
- (g) Coefficient of shear deflection (C). For calculating uniform load and center-point load deflections of the I-joist in a simple-span application, use Eqs. 1 and 2.

$$\text{Uniform Load: } \delta = \frac{22.5 \omega \ell^4}{EI} + \frac{\omega \ell^2}{C} \quad [1]$$

$$\text{Center-Point Load: } \delta = \frac{36 P \ell^3}{EI} + \frac{2 P \ell}{C} \quad [2]$$

Where:

- δ = calculated deflection (in.),
- ω = uniform load (lbf/ft),
- ℓ = design span (ft),
- P = concentrated load (lbf),
- EI = bending stiffness of the I-joist (lbf-in.²), and
- C = coefficient of shear deflection (lbf-ft/in.).

APA – The Engineered Wood Association is an accredited certification body under ISO 65 by Standards Council of Canada (SCC) and an accredited inspection agency by the International Code Council (ICC) International Accreditation Service (IAS) under ISO/IEC 17020. APA is also an accredited testing organization recognized by IAS and SCC under ISO/IEC 17025. APA is a recognized testing laboratory by Miami-Dade County, and a Product Testing Laboratory, Product Quality Assurance Entity, and Product Validation Entity by the Florida Department of Community Affairs (DCA).

**APA – THE ENGINEERED WOOD ASSOCIATION
HEADQUARTERS**

7011 So. 19th St. ▪ Tacoma, Washington 98466
Phone: (253) 565-6600 ▪ Fax: (253) 565-7265 ▪ Internet Address: www.apawood.org

PRODUCT SUPPORT HELP DESK
(253) 620-7400 ▪ *E-mail Address:* help@apawood.org

DISCLAIMER

APA Product Report® is a trademark of *APA – The Engineered Wood Association*, Tacoma, Washington. The information contained herein is based on the product evaluation in accordance with the references noted in this report. Neither APA, nor its members make any warranty, expressed or implied, or assume any legal liability or responsibility for the use, application of, and/or reference to opinions, findings, conclusions, or recommendations included in this report. Consult your local jurisdiction or design professional to assure compliance with code, construction, and performance requirements. Because APA has no control over quality of workmanship or the conditions under which engineered wood products are used, it cannot accept responsibility of product performance or designs as actually constructed.